X-band Structure Production History

Tug Arkan
AAC Meeting
November 19th, 2003

Outline

- RF Structure Factory Infrastructure
- FXA type RF Structures
- FXB type RF Structures

Infrastructure (will be seen on Tour)



Structure Assembly Clean Room

(Class 1000)

Proper Clean Room Attire



Infrastructure



RF Quality Control Clean Room

(Class 3000)

A Structure during Bead-Pull Measurements & Tuning



Infrastructure



Small Vacuum Furnace:

- •Installed in FY01
- •All molybdenum hot zone
- 12 inch x 12 inch x 15 inch
- •Dry Roughing Pump & CRYO Pump
- •1200 degree C max temperature




Large Vacuum Furnace:

- •Installed in FY02
- •All molybdenum hot zone (Recently purchased from Schwarzkopf Technologies)
- 20 inch x 100 inch
- •Dry Roughing Pump & CRYO Pump
- •1200 degree C max temperature










FXA type RF Structures


- We have produced three 20-cm long (short length) traveling wave, detuned, constant gradient structures: FXA-001, FXA-002 and FXA-003:
 - These structures were not high power tested. They were produced to evaluate the feasibility of the Factory Infrastructure and to learn & gain experience in RF structure fabrication
- Design is identical to SLAC T20VG5 structure (except brazing grooves in the disks)
- All brazed structures, no diffusion bonding
- Disks are precision machined, no diamond turning [industrial vendors]
- Couplers are precision machined with some diamond turned RF surfaces (iris area) [industrial vendors]

FXA type RF Structures

- FXA-001 was brazed at an outside furnace company
- FXA-002 couplers were brazed in Fermilab Small vacuum furnace and the rest of the brazing was completed at an outside furnace company
- FXA-003 was totally brazed and fabricated at Fermilab vacuum furnaces









0.89 mm diam.

brazing wire







FXB type RF Structures

- We have produced six 60-cm long (full length) traveling wave, detuned, constant gradient structures: FXB-002 thru FXB-007
 - Except FXB-005, all the FXB structures were high power tested at NLCTA, SLAC
- We have produced 9 full length dummy (no iris) structures for Girder Studies
- Design is identical to SLAC H60VG3 structure (except brazing grooves in the disks)
- All brazed structures, no diffusion bonding
- Disks & Couplers are precision machined, no diamond turning (industrial vendors)

From FXA to FXB structures:


- Disk OD is increased from 45 mm to 61mm
- Structure length is increased from 20 cm to 60 cm
- Disk & Coupler Etching with SLAC C01 procedure
- Strict Clean Room Working Procedures
- Traveler Development (it is currently fully implemented & controlled)
- Improvements from Structure to Structure
 - Fermilab Coupler Design (Fat lipped couplers, Wave guide couplers)
 - Fabrication Procedure



FXB-002 and some of us from Fermilab RF Structures Group @ NLCTA









High Power Test Results

From C. Adolphsen, SLAC

